

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTU
Inte

WO 9604216A1

INTERNATIONAL APPLICATION PUBLISHED

(51) International Patent Classification ⁶ :

C03C 17/34, G02C 7/10

A1

(43) International Publication Date: 15 February 1996 (15.02.96)

(21) International Application Number: PCT/US95/08612

(22) International Filing Date: 10 July 1995 (10.07.95)

(30) Priority Data:

08/283,009

29 July 1994 (29.07.94)

US

(71) Applicant: BAUSCH & LOMB INCORPORATED [US/US];
One Chase Square, P.O. Box 54, Rochester, NY 14601-0054
(US).(72) Inventors: ARDEN, Amy, J.; Apartment 12, 76 East Boule-
vard, Rochester, NY 14610 (US); CUMBO, Michael, J.; 18
Westfield Commons, Rochester, NY 14625 (US).(74) Agents: POLYN, Denis, A. et al.; Bausch & Lomb Incor-
porated, One Chase Square, P.O. Box 54, Rochester, NY
14601-0054 (US).(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ,
EE, FI, GE, HU, IS, JP, KG, KP, KR, KZ, LK, LR, LT,
LV, MD, MG, MN, MX, NO, NZ, PL, RO, RU, SG, SI,
SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT,
BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL,
PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,
ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD,
SZ, UG).

Published

With international search report.

(54) Title: LIGHT-ABSORBING AND ANTI-REFLECTIVE COATING FOR SUNGLASSES

(57) Abstract

A sunglass lens having improved anti-reflection and transmittance comprises a lens-shaped substrate and a coating formed on the concave surface of the lens. The first layer deposited adjacent to the concave surface of the lens comprises a titanium suboxide material, the second layer comprises a material having a high refractive index, and the third layer comprises a material having a low refractive index.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

LIGHT-ABSORBING AND ANTI-REFLECTIVE COATING FOR SUNGLASSES**BACKGROUND OF THE INVENTION**

The present invention relates to sunglass lenses having a multilayer coating, with improved transmittance and anti-reflection characteristics.

Sunglass lenses can be classified according to two general categories, general purpose sunglasses and special purpose sunglasses.

For both categories of sunglasses, it is important that the lenses provide a desired transmittance of light in the visible region. Standards for general purpose sunglass lenses indicate that the lens provides a luminous transmittance between 8% to 40%, and permits recognition of red, green and yellow traffic signal colors so that the lenses are suitable for driving conditions. Special purpose sunglasses are designed to function in more extreme conditions, and generally have a lower transmittance than general purpose sunglasses. Since the lenses of this latter class are designed for special purposes, the lenses do not need to pass color recognition tests.

One type of general purpose sunglass lenses is photochromic lenses, i.e., the transmittance varies with intensity of incident light and ambient temperature. For this type of lens, it is desirable that the lens meets the transmittance standards for general purpose sunglasses under normal use conditions.

-2-

For sunglass lenses, it is also important that reflection of visible light at the concave (or rear) lens surface is sufficiently low to avoid glare from incident light at the concave surface.

U.S. Patent No. 4,802,755 (Hensler) describes a dual-purpose photochromic lens, i.e., the lens functions as a general purpose lens at 20°C and as a special purpose lens at 0°C. The described lens is illustrative of a sunglass lens having very desirable transmittance and anti-reflective characteristics. More specifically, the lens has a photochromic glass substrate and a transmittance of approximately 10% at 20°C in bright sunlight, wherein the overall transmittance of the substrate is reduced by coating both the convex (front) and concave (rear) surfaces with a titanium monoxide material. An anti-reflective magnesium fluoride layer is applied to the titanium monoxide layer on the concave surface.

The present invention provides a sunglass lens having improved transmittance and anti-reflection characteristics. This is accomplished using a multilayer coating that combines optical absorption and interference effects to reduce both the transmittance and concave surface reflection of the lens.

SUMMARY OF THE INVENTION

The invention relates to a sunglass lens comprising: a substrate in the shape of a lens; a first layer deposited adjacent to the concave surface of the lens, the first

-3-

layer comprising TiO_x wherein x is about 0.2 to 1.5; a second layer deposited adjacent to the first layer comprising a material having a refractive index of about 1.80 to 2.50; and a third layer deposited adjacent to the second layer and comprising a material having a refractive index of about 1.35 to 1.60.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is an enlarged partial sectional view of a preferred embodiment of the invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

The Figure illustrates an embodiment of the invention. The substrate 10 on which the coating is applied has the form of a lens. The lens material may be glass or plastic. A first layer 1 is deposited adjacent to the lens 10 on the concave (rear) surface. A second layer 2 is deposited adjacent to the first layer 1, and a third layer 3 is deposited adjacent to the second layer 2.

Layer 1 comprises TiO_x wherein x is about 0.2 to 1.5. Layer 1 partially absorbs light passing therethrough, thereby reducing transmittance of light, including light in the visible region of 400 to 700 nm. Preferably, this layer is selected so that it reduces transmittance of light therethrough by at least 10%, more preferably at least 20%. Generally, the thickness of layer 1 will be about 10 to 40 nm.

-4-

The imaginary part of the refractive index (k) of layer 1 is preferably in the range of about 0.2 to 2.4; this ensures adequate absorption. Additionally, the real part of the refractive index (n) of layer 2 is preferably in the range of about 1.50 to 2.50, more preferably in the range of about 1.60 to 2.00. (For comparison, a layer formed of TiO_2 has a k value that is near zero at all visible wavelengths, and an n value which is in the range of 2.2 to 2.5.)

Layer 1 may be deposited directly on the lens by methods generally known in the art, such as physical vapor deposition or chemical vapor deposition. Both oxygen and nitrogen are included in the reaction chamber to obtain a layer formed primarily of TiO_x , although the process may result in formation of other materials, such as titanium nitrides. By varying the pressures of the oxygen and nitrogen, the composition of the absorption layer can be optimized to obtain a layer having the desired optical properties. Additionally, transmittance of the lens can be controlled by varying the thickness of layer 1.

It is further preferred that the coated lens has a luminous transmittance between 8% to 40% (as determined by the American National Standard Institute, Inc., ANSI Z80.3-1986, incorporated herein by reference) and meets these ANSI requirements for recognition of red, green and yellow traffic signal colors so that the lenses are suitable for wear during driving.

Layer 2 is deposited adjacent to layer 1, and layer 3 is deposited adjacent to layer 2. Layer 2 comprises a material having a high refractive index (n), i.e., a refractive index of about 1.80 to 2.50. Representative materials include Ta_2O_5 , TiO_2 , ZrO_2 and HfO_2 . Layer 3 comprises a material having a low refractive index (n), i.e., a refractive index of about 1.35 to 1.60. Representative materials include MgF_2 and SiO_2 . Other materials having the high or low refractive index are known in the art. Layer 2 and 3 may be deposited by methods known in the art, such as physical vapor deposition or chemical vapor deposition. Generally, the third layer will have its interface with air, as shown in the embodiment of FIG. 1.

The materials and thicknesses of the second and third layers are selected so that these layers effectively reduce reflection at the concave (rear) lens surface. Generally, the physical thickness of layer 2 may be about 90 to 180 nm, and the physical thickness of layer 3 may be about 70 to 120 nm.

The transmittance of the lens will be dependent primarily on the thickness and k value of layer 1. Based on these parameters of layer 1, standard computer models can be used to determine optimum film thickness and n values of layers 2 and 3 to achieve anti-reflection, as will be evident to one skilled in the art.

Glare at the concave (rear) lens surface results from reflection of incident light at the concave surface. For

-6-

an uncoated lens, a portion of incident light at the concave lens surface would be reflected from the concave surface of the lens towards the wearer's eye, and additionally, a portion of the non-reflected light passing through the lens would be reflected from the convex surface of the lens toward the wearer's eye.

In the present invention, reflectance at the concave lens surface is minimized since layers 2 and 3 are chosen to provide effective anti-reflection. Additionally, layer 1 further reduces reflected light. More specifically, this absorbing layer significantly increases the bandwidth of the anti-reflection coating. (This is an important consequence of layer 1 having a non-zero imaginary component of the refractive index (k).) Any non-reflected light at the concave surface must pass through layer 1 twice, once upon entering the coating, and again after passing through the lens and being reflected at the convex surface. It will be appreciated that each pass through layer 1 reduces transmittance of light therethrough.

According to the invention, luminous reflectance at an interface of said coating with air is no greater than 2%, preferably, no greater than 1%. Luminous reflectance is defined as the specular reflectance weighted by the photopic response of the eye, and may be calculated by methods disclosed in the aforementioned ANSI Z80.3-1976 standards.

Specific preferred embodiments are illustrated in the following examples.

EXAMPLES 1 AND 2

Representative coatings are shown in Tables 1 and 2. Each coating is designed for a lens made of a borosilicate glass having a neodymium oxide as a major colorant described in U.S. Patent No. 5,190,896 (Pucilowski et al.) and which has a refractive index (n) of about 1.59 at a design wavelength of 550 nm.

TABLE 1

<u>Layer</u>	<u>Material</u>	<u>Physical Thickness (nm)</u>
10	glass	--
1	TiO _x	17.0
2	Ta ₂ O ₅	61.0
3	MgF ₂	90.6
air	--	--

TABLE 2

<u>Layer</u>	<u>Material</u>	<u>Physical Thickness (nm)</u>
10	glass	--
1	TiO _x	32.8
2	TiO ₂	43.2
3	MgF ₂	90.6
air	--	--

EXAMPLE 3

An additional representative coating is shown in Table 3. The coating is designed for a lens made of the photochromic borosilicate glass described in U.S. Patent

-8-

No. 4,802,755 which has a refractive index (n value) of about 1.523 at a design wavelength of 550 nm.

TABLE 3

<u>Layer</u>	<u>Material</u>	<u>Physical Thickness (nm)</u>
10	glass	--
1	TiO _x	32.8
2	TiO ₂	43.2
3	MgF ₂	90.6
air	--	--

Table 4 lists luminous transmittance, and luminous reflectance at the concave (rear) surface. For comparison purposes, these properties for a lens described in U.S. 4,802,755 is listed as the Comparative Example.

TABLE 4

	<u>% Luminous Transmittance</u>	<u>% Luminous Reflectance</u>
Ex. 1	14.34	1.23
Ex. 2	13.38	0.89
Ex. 3	19.98	1.23
Comp. Ex.	19.32	7.75

The examples illustrate that the present invention provides sunglass lenses having very desirable transmittance and anti-reflection characteristics, and that the coatings may be applied to lens substrates with

-9-

the coatings may be applied to lens substrates with different refractive index (n) values. Also, the coated lens of Example 3, corresponding to the present invention, exhibited similar transmittance but significantly less luminous reflectance at the concave surface than the lens made in accordance with U.S. 4,802,755.

A wide range of materials may be used for the lens substrate, especially plastic or glass (including photochromic glasses). Generally, the coating will not impart a change to the visible appearance of the lens material other than darkening. Preferably, the lens material is chosen so that it provides effective UV blocking.

It will be appreciated that no coatings are required on the convex (front) surface of the lens, affording reduced costs in manufacturing. Also, if desired, optional coatings can easily be formed on the convex surface, such as a hard coating or a scratch-resistant coating.

Although certain preferred embodiments have been described, it is understood that the invention is not limited thereto and modifications and variations would be evident to a person of ordinary skill in the art.

We claim:

-10-

1. A sunglass lens comprising:
 - a substrate in the shape of a lens;
 - a first layer deposited adjacent to the concave surface of the lens, said first layer comprising TiO_x wherein x is about 0.2 to 1.5;
 - a second layer deposited adjacent to the first layer, said second layer comprising a material having a refractive index of about 1.80 to 2.50; and
 - a third layer deposited adjacent to the second layer, said second layer comprising a material having a refractive index of about 1.35 to 1.60.
2. The sunglass lens of claim 1, wherein the second layer comprises a material selected from the group consisting of Ta_2O_5 , TiO_2 , ZrO_2 and HfO_2 .
3. The sunglass lens of claim 1, wherein the third layer comprises a material selected from the group consisting of MgF_2 and SiO_2 .
4. The sunglass lens of claim 1, wherein the second layer comprises Ta_2O_5 and the third layer comprises MgF_2 .
5. The sunglass lens of claim 1, wherein the first layer has an n value ranging from about 1.50 to 2.50.
6. The sunglass lens of claim 1, wherein the first layer has a k value ranging from about 0.2 to 2.4.
7. The sunglass lens of claim 1, having no coating on the convex surface of the lens.
8. The sunglass lens of claim 1, wherein the lens is formed of glass.

-11-

9. The sunglass lens of claim 1, wherein the lens is formed of plastic.

10. The sunglass lens of claim 1, wherein said first layer reduces transmittance of light therethrough by at least 10%.


11. The sunglass lens of claim 1, wherein luminous reflectance at an interface of said coating with air is no greater than 2%.

12. The sunglass lens of claim 11, wherein the sunglass lens has a luminous transmittance between 8 to 40%.

13. The sunglass lens of claim 1, wherein luminous reflectance of visible light at an interface of said coating with air is no greater than 1%.

14. The sunglass lens of claim 13, wherein the sunglass lens has a luminous transmittance between 8 to 40%.

1/1



INTERNATIONAL SEARCH REPORT

Internat. Application No
PCT/US 95/08612

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C03C17/34 G02C7/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C03C G02C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 409 719 (ETABLISSEMENTS PIERRE ANGENIEUX) 23 January 1991 see claim 1; figures 4,5 ---	1-14
A	GB,A,2 247 691 (GLAVERBEL) 11 March 1992 see abstract ---	1
A	CH,A,558 763 (BATTELLE MEMORIAL INSTITUTE) 14 February 1975 see claim 1; figure 4 ---	
A	US,A,4 261 645 (CANON KK) 14 April 1981 see claim 1; figure 6 ---	1-14
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

30 October 1995

Date of mailing of the international search report

27. 11. 95

Name and mailing address of the ISA

European Patent Office, P.B. 3818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Reedijk, A

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/US 95/08612

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 110, no. 7, 3 April 1989 Columbus, Ohio, US; abstract no. 119994g, page 338; see abstract & CS,A,251 633 (M. HORKY ET AL.15-04-1988) ----	2,3
A	DE,A,41 24 937 (O.I.B. GMBH OPTISCHE INTERFERENZ BAUELEMENTE) 26 March 1992 see column 2, line 50 - column 3, line 22; claim 1 -----	1-3

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/08612

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-409719	23-01-91	FR-A- 2650083 JP-A- 3064730	25-01-91 20-03-91
GB-A-2247691	11-03-92	BE-A- 1005317 CH-A- 682745 DE-A- 4128600 ES-A- 2049135 FR-A- 2666325 IT-B- 1249989 JP-A- 4270144 LU-A- 87997 NL-A- 9101446 SE-D- 501632 SE-A- 9102490 US-A- 5203903	29-06-93 15-11-93 05-03-92 01-04-94 06-03-92 30-03-95 25-09-92 03-03-92 16-03-92 03-04-95 01-03-92 20-04-93
CH-A-558763	14-02-75	NONE	
US-A-4261645	14-04-81	JP-C- 1336520 JP-A- 54098257 JP-B- 60051081 DE-A- 2901675	11-09-86 03-08-79 12-11-85 26-07-79
DE-A-4124937	26-03-92	NONE	